



GROUP	THICKNESS INCH (mm)	WIDTH INCH (mm)	LENGTH INCH (mm)	WEIGHT LBS (kg)
Solid	1/4" (6 mm)	30"(760 mm)	98" (2,500 mm)	42.5 lbs (19.3 kg)
	1/2" (12 mm)		145" (3,680 mm)	125.0 lbs (56.7 kg)
Sanded	1/4" (6 mm)	30"(760 mm)	98" (2,500 mm)	41.3 lbs (18.7 kg)
	1/2" (12 mm)		145" (3,680 mm)	121.6 lbs (55.1 kg)
Aspen	1/4" (6 mm)	30"(760 mm)	98" (2,500 mm)	42.1 lbs (19.1 kg)
	1/2" (12 mm)		145" (3,680 mm)	123.7 lbs (56.1 kg)
Pebble	1/2" (12 mm)	30"(760 mm)	145" (3,680 mm)	114.0 lbs (51.7 kg)
Quarry	1/2" (12 mm)	30"(760 mm)	145" (3,680 mm)	116.4 lbs (52.8 kg)
Tempest	1/2" (12 mm)	30"(760 mm)	145" (3,680 mm)	117.3 lbs (53.2 kg)

- 1/4" (6mm) thick sheet is generally not recommended for countertops or other horizontal applications.

*This Technical Bulletin is intended to provide guidelines for optimal fabrication, installation, and performance of LOTTE ADVANCED MATERIALS products mentioned. Though the information contained herein is deemed reliable, none of the contents--including but not limited to the instructions, techniques, graphics, and recommendations--is to be understood as implying legal liability of fitness for a specific purpose, any other type of warranty, or being complete or absolute in its range and nature of information.*

*Depending on the user's particular application, all necessary measures must be taken to verify and test the adequacy for such needs or application. Any information or recommendation herein is strictly for purposes of reference and as such, LOTTE ADVANCED MATERIALS assumes no responsibility for its suitability or accuracy or the use of such information for products other than LOTTE ADVANCED MATERIALS Staron® solid surfaces & Radianz® quartz surfaces.*