


MELATONE LTD.

692-10, GOJAN-DONG, NAM DONG-KU INCHEON, KOREA

- ITEM : Metal H.P.L.
- DATE : 2007. 5. 01. ~ 5. 07.
- TEST METHOD : Korean Standards Association(KSA M 3803)

TEST ITEM		STANDARD	TEST RESULTS
1.Appearance		No Change In Appearance	No Change In Appearance
2.Dimension Stability	Absorption	No Defect	No Defect
	Width Direction	Less Than 1.4 %	0.6 %
	Length Direction	Less Than 1.1 %	0.5 %
3.Stain Resistance	Gasoline	No Defect	No Defect
	Ethanol		No Defect
	Soap Solution		No Defect
	10% Ammonium Solution		No Defect
	10% Citrate		No Defect
	Acid Solution		No Defect
4.Flexibility		No Defect	No Defect
5.Surface Wear Resistance	Wear value	More Than 200	989
	Wear amount	Less Than 0.1	0.05
6.Light Resistance		No Defect	No Defect
		Less Than 3.0	0.4
7.Ball Impact Resistance (mm)		More Than 100	No Defect

- INSPECTOR : Yong Sun, Cha 

- Representative : Yang Han. Lee 



Melatone

692-10 Gojan-dong, Namdong-ku, Incheon, Korea
 (Namdong Industrial Area:122B/11L)
 TEL: 82-32-811-8620~4, 82-32-818-2347~9
 Fax: 82-32-811-8625
<http://www.melatone.co.kr>

Melacore
 Decorative Laminates
 Metal Laminates
 Veneer Laminates
 Phenolic Back up Board
 Laminate Flooring
 Conductive HPL
 Fiber & Botanic Laminates